

## PRODUCT DATA SHEET

# Sarnaplast®-2235

Sealant for Sarnafil® flat roof systems

## DESCRIPTION

Sarnaplast®-2235 is a 1-part clear elastomeric silicone sealant for sealing connection details on Sarnafil® flat roof systems.

## USES

Sarnaplast®-2235 may only be used by experienced professionals.

A Sealant to seal:

- Flashing joints
- Expansion joints
- Perimeter flashings

## CHARACTERISTICS / ADVANTAGES

- Resistant to UV exposure
- Application onto rough and smooth substrates
- Bonds to most construction materials
- Applied using standard sealant gun



## PRODUCT INFORMATION

Chemical Base	Silicone with neutral hardening system (Alkoxy)
Packaging	310 ml cartridge, 12 cartridges per box
Appearance / Colour	Clear
Shelf Life	21 months from date of production
Storage Conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.
Density	~ 0,98 g/cm <sup>3</sup> (+25 °C)

## SYSTEM INFORMATION

Compatibility	Compatible substrates/products	concrete, brick, plaster, metal, glass, ceramic, Sarnafil® TG/TS, Sarnafil® G/S
	Ancillary products	Primer T-501 Primer-110 Sarna® Cleaner

## APPLICATION INFORMATION

Ambient Air Temperature	+5 °C min
Substrate Temperature	+5 °C min
Curing Time	Skinning time ~ 30 minutes. Completely cured ~7 days.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTS

### Installation instructions

Refer to 'Sarnafil® and Sikaplan® flat roof waterproofing membranes'

## LIMITATIONS

Installation work must only be carried out by Sika® trained and approved contractors, experienced in this type of application.

- Installation of ancillary products, e.g. contact adhesives / cleaners is limited to temperatures above +5 °C. Refer to relevant Product Data Sheets for further information.

## ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

The substrate should be of sufficient strength to resist the stresses induced by the sealant during movement.

### SUBSTRATE PREPARATION

The substrate must be sound, clean, dry and free of all contaminants such as dirt, dust, algae or other deleterious matter which could affect adhesion of the sealant. All dust, loose and friable material must be completely removed from all surfaces before application of any activators, primers or sealant.

### APPLICATION

#### Membrane Installation Procedure

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions.

#### Sealing Procedure

##### Priming

Prime the substrates with either Primer 110 (Sarnafil® G/S) or Primer T 501 (Sarnafil® TG/TS) and allow to dry.

##### Application

Prepare the end of the cartridge before or after inserting into the sealant gun then fit the nozzle. Extrude

Sarnaplast®-2235 into or around the joint ensuring that it comes into full contact with the sides of the joint and avoiding any air entrapment.

#### **Finishing**

As soon as possible after application, sealant must be firmly tooled against the joint sides to ensure adequate adhesion and the required finish.

Use a compatible tooling agent such as water to smooth the joint surface. Do not use tooling products containing solvents.

#### **CLEANING OF TOOLS**

Clean all tools and application equipment immediately after use with Sarna Cleaner. Once cured, hardened material can only be removed mechanically.

#### **LOCAL RESTRICTIONS**

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

#### **Sika Pakistan (Pvt.) Limited**

141-CCA Phase IV, DHA

Lahore Punjab 54792

Pakistan

phone: +92 42 3569 4266 - 67

fax: +92 42 3569 4268

<http://pak.sika.com/>

#### **PRODUCT DATA SHEET**

Sarnaplast®-2235

May 2021, Version 01.01

020945072150000002

Sarnaplast-2235-en-PK-(05-2021)-1-1.pdf